

DATA SHEET

TAM 4000	
Typical Applications:	Extrusion Dies Die Casting Components Electro Forging & Upsetting Riveting Dollies
Nominal Composition:	90% W – 4% Ni – 2% Fe – 4% Mo
Density:	17.1 gm/cm ³
Hardness:	28 HRC
Ultimate Tensile Strength	870 N/mm ²
Elongation:	5 %
Magnetic Properties:	Weakly Ferro Magnetic