

DATA SHEET

TAM 3950	
Spec:	ASTM B777-07 Class 3
Typical Applications:	Ballast & Balancing
Nominal Composition:	95% W – 3.5% Ni – 1.5% Fe
Density:	18gm/cm ³
Hardness:	27 HRC
Ultimate Tensile Strength	870 N/mm ²
Elongation:	7 %
Magnetic Properties:	Weakly Ferro Magnetic